



KORAKOD 66 CO.,LTD.

Major Branch and Office:

No. 7 Soi Petchkasem 32, Petchkasem Rd, Pakklong Pasichareon, Pasichareon District,
Bangkok Thailand, 10160

Tel : +662 8685807-8

Fax : +662 8685608

Email : korakod66@gmail.com

Company Introduction

KORAKOD 66 was established in 2007 as a supplier for Petroleum products based in Thailand. With the company effort to become the leading supplier in the category, we have become the authorized distributors for various Thai refineries in the modern day. In achieving the goal to be the top supplier in one category, we put all our efforts and dedicate to wax business. Currently, KORAKOD 66 supplies petroleum waxes for both domestic and international markets. We have expanded our markets to overseas in recent years, and now our company becomes strategic partnership with customers in various countries and regions such as China, India, Japan, UAE, South Africa, Australia, and USA. Professionalism and knowhow are our key assets for international transactions. We maintain long term relationships through understanding and effective communication. Our commitment is to maintain our agreements with you. KORAKOD 66 has the vision to become the most reliable and trustworthy wax supplier for our clients through valuation of mutual benefits for both parties in order to create a win-win situation for our partnerships.

Products

KORAKOD 66 supplies the various wax grades to cover different applications as may require from our partners. Currently we serve our products to different industries such as pharmaceutical, cosmetics, artificial wood or particle board, emulsion wax, adhesive, paper, polishing, and candles industries. Our products include:

- Slack Wax 150 Grade
- Slack Wax 500 Grade
- Bright Stock Slack Wax (BSSW) White color (L1.0)
- Bright Stock Slack Wax (BSSW) Yellow color (L2.5)
- Fully Refined Paraffin Wax 58/60
- Semi Refined Paraffin Wax 60/62
- Slack Wax DAO Grade



KORAKOD 66 CO.,LTD.

No.7 Soi Phetkasem32, Phetkasem Road, Pakklongpasichareon, Pasichareon, Bangkok, Thailand 10160
เลขประจำตัวผู้เสียภาษี 3 0337 6812 1

SLACK WAX 150 GRADE:



Component	Method	Units	Specification	Result
Congealing Point	ASTM D-938	Deg C	51 - 58	54.2
ASTM Color	ASTM D-1500	-	.5 Max	L 0.5
Density@ 15 °C	ASTM D-1298	Kg/l	Report	0.8173
Cone Penetration at 25°C	ASTM D-937	1/10 mm	Report	17
Flash Point (COC)	ASTM D-92	Deg C	Min.200	230
Oil in Wax	ASTM D-721	% wt	Max. 10	2.10
Kinematic Viscosity @ 100 °C	ASTM D-445	cSt	2.5 - 5.5	3.790

KORAKOD 66 CO.,LTD.

No.7 Soi Phetkasem32, Phetkasem Road, Pakklongpasichareon, Pasichareon, Bangkok, Thailand 10160
เลขประจำตัวผู้เสียภาษี 3 0337 6812 1

Slack Wax 500 Grade



Component	Method	Units	Specification	Result
Congealing Point	ASTM D-938	Deg C	60 - 67	64.0
ASTM Color	ASTM D-1500	-	.5 Max	L 0.5
Density@ 15 °C	ASTM D-1298	Kg/l	Report	0.8403
Cone Penetration at 25°C	ASTM D-937	1/10 mm	Report	22
Flash Point (COC)	ASTM D-92	Deg C	Min.200	270
Oil in Wax	ASTM D-721	% wt	Max. 13	3.55
Kinematic Viscosity @ 100 °C	ASTM D-445	cSt	6 - 9	7.642

KORAKOD 66 CO.,LTD.

No.7 Soi Phetkasem32, Phetkasem Road, Pakklongpasichareon, Pasichareon, Bangkok, Thailand 10160
เลขประจำตัวผู้เสียภาษี 3 0337 6812 1

Bright Stock Slack Wax L1 Grade



Component	Method	Units	Specification	Result
Congealing Point	ASTM D-938	Deg C	Report	75.0
ASTM Color	ASTM D-1500	-	Max.1.5	L 0.5
Density@ 15 °C	ASTM D-1298	Kg/l	Report	0.8633
Cone Penetration at 25°C	ASTM D-937	1/10 mm	Report	22
Flash Point (COC)	ASTM D-92	Deg C	Min.200	314
Oil in Wax	ASTM D-721	% wt	Max. 10	2.82
Kinematic Viscosity @ 100 °C	ASTM D-445	cSt	15.0-20.0	17.46

KORAKOD 66 CO.,LTD.

No.7 Soi Phetkasem32, Phetkasem Road, Pakklongpasichareon, Pasichareon, Bangkok, Thailand 10160
เลขประจำตัวผู้เสียภาษี 3 0337 6812 1

Bright Stock Slack Wax L2.5 Grade



Component	Method	Units	Specification	Result
ASTM Color	ASTM D-1500	-	Max.4.0	L 2.5
Oil in Wax	ASTM D-721	% wt	Max. 10	3.72
Drop Melting Point	ASTM D-127	Deg C	Report	79.80
Density@ 15 °C	ASTM D-1298	Kg/l	Report	0.8645
Flash Point (COC)	ASTM D-92	Deg C	Min.250	312
Kinematic Viscosity @ 100 °C	ASTM D-445	cSt	15.0-20.0	17.60

Packaging

Also, we emphasize that under different environments, capacities, and objectives, the packaging should be flexible enough to fit with different conditions. Therefore, KORAKOD 66 has developed and provided various types of packaging to increase the convenience and suitability for each of our clients. Below are examples of packaging we provide:

Contact Us

It would be our pleasure to serve and service to you. If you interest in our products, please kindly contact:



Name: Mr. Saratoon WUTHISAKSILP

Position: Business Development Manager

Phone Number: +66(8)1 9067733

Email: saratoon@korakod66.com